



ESL ELECTROSCIENCE

CERAMIC TAPES &
THICK-FILM MATERIALS

416 EAST CHURCH ROAD
KING OF PRUSSIA, PA 19406-2625, U.S.A

T: 610-272-8000
F: 610-272-6759

www.electroscience.com

CERMET GOLD CONDUCTOR

8835 VF-G

Lead and Cadmium-Free*

ESL 8835 VF-G has been designed as a high solids content gold conductor and is used for filling via posts in complex multilayer circuits. This conductor is compatible with the 4905-C series dielectrics and will not shrink or crack when subjected to multiple firing. It is available in two different viscosities and is therefore able to fulfil a wide range of customer requirements.

The lower viscosity version of 8835 VF-G can also be used for through hole printing in laser drilled holes and does not exhibit shrinkage cracking or adhesion problems after firing.

PASTE DATA

Rheology:	Thixotropic, screen-printable paste
Viscosity: (Brookfield RVT, 10rpm, ABZ spindle, 25.5 ± 0.5 °C)	150 ± 30 Pa.s 275 ± 25 Pa.s
Bonding Mechanism:	Mixed-bonded
Shelf Life (20 - 25 °C):	6 months

PROCESSING

Screen Mesh, Emulsion:	325 S/S, 15 µm
Levelling Time (at 20°C):	5 - 10 min
Drying Time (at 125°C):	10 -15 min
Firing Temperature Range:	850 - 1000°C in air
	Optimum: 850 °C
	Time at peak: 10 min
Total Firing Cycle:	1 hour
Substrate for Calibration:	96% alumina
Thinner:	ESL 401

ESL Europe 8835 VF-G 0406-A

ESL Affiliates

ESL Europe (Agmet Ltd) • 8 Commercial Road • Reading • Berkshire • England • RG2 0QZ • Tel: +44 (0) 118 918 2400 • Fax: +44 (0) 118 986 7331 • Sales@ESLEurope.co.uk

ESL Nippon • Sukegawa Bldg. • 6th floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: +81-3-3864-8521 • Fax: +81-3-3864-9270 • Sales@ESL-Nippon.co.jp

ESL China • Room #1707, Tower A, City Center of Shanghai • 100 Zunyi Road • Shanghai, China 200051 • Tel: +86-21-6237-0336 and 0337 • Fax: +86-21-6237-0338
ESLChina@eslshanghai.net

See Caution and Disclaimer on other side.

TYPICAL PROPERTIES

Fired Thickness:

(measured on a 2 mm x 2 mm pad on 96% alumina)

20 ± 5 µm

Approximate Coverage:

95 cm²/g

Resistivity:

< 30 mΩ/□

ESL Europe 8835 VF-G 0406-A

*Complies with RoHS, ELV, WEEE and CHIP 3 EC directives.

CAUTION: Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapours emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

DISCLAIMER: The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. ElectroScience assumes no liability for any injury, loss, or damage, direct or consequential, arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make his own tests to determine the suitability thereof for his particular use, before using it. User assumes all risk and liability whatsoever in connection with his intended use. ElectroScience's only obligation shall be to replace such quantity of the product proved defective.
